

PROPERTIES OF SODA-LIME SILICA FLOAT GLASS

ATS-129
09/2026

Mechanical Properties

Modulus of Rupture (MOR): tensile stress at fracture originating in the glass surface, not in the scored and cut-glass edge, for 60-Second load duration on weathered, in-service, glass.

Typical Mean MOR (50% probability of breakage)

Glass Kind	Mean MOR (psi)	Mean MOR (MPa)
Annealed	6,000	41
Heat-Strengthened	12,000	83
Fully Tempered	24,000	165

Typical Design Stress (0.8% probability of breakage)

Glass Kind	Mean MOR (psi)	Mean MOR (MPa)
Annealed	2,800	19
Heat-Strengthened	5,600	39
Fully Tempered	11,200	77

Modulus of Elasticity (Young's) 10.4 x 10⁶ psi (72 GPa)

Modulus of Rigidity (Shear) 4.3 x 10⁶ psi (30 GPa)

Bulk Modulus 6.2 x 10⁶ psi (43 GPa)

Poisson's Ratio 0.22

Density 156 lb/ft³ (2500 kg/m³)

Coefficient of Thermal Stress 50 psi/°F (0.62 MPa/°C)

Thermal Conductivity at 75°F 6.5 Btu.in/hr.°F.ft² (0.937 W.m/m².°C)

Specific Heat at 75° F 0.21 Btu/lb_m.°F (0.88 kJ/kg.°C)

Coefficient of Linear Expansion (75-575°F) 4.6 x 10⁻⁶ in/in.°F (8.3 x 10⁻⁶ mm/mm.°C)

e.g. 200" of glass heated 100 °F expands 0.09"

Hardness (Moh's Scale)	5-6
Softening Point (ASTM C338)	1319°F (715°C)
Pilkington Optiwhite ™ ~732°C Log η = 6.6	
Annealing Point (ASTM C336)	1018°F (548°C)
Pilkington Optiwhite ™ ~559°C Log η = 12.0	
Strain Point (ASTM C336)	952°F (511°C)
Pilkington Optiwhite ™ ~526°C Log η = 13.5	

Where Log η = Viscosity (Pa.s)

Index of Refraction:

(0.5893 μm , Sodium D Line)	1.523
(1 μm)	1.511
(2 μm)	1.499
Emissivity (Hemispherical) at 75°F	0.84

Stress-Optical Coefficient Stress (psi) = 2.18 x Retardation (μm) / thickness (in)

Raw Materials Used in Typical Float Glass

Sand	Soda Ash	Limestone	Dolomite	Salt Cake	Cullet (Recycled Glass)
SiO ₂	Na ₂ CO ₃	CaCO ₃	MgCa(CO ₃) ₂	Na ₂ SO ₄	

Recycled Materials

The float glass process recycles virtually all the glass waste from the in-plant production melting and cutting processes. This broken glass, known as cullet, is reintroduced with the raw materials batch mix in the furnace as an aid to melting. It takes half the amount of energy to produce glass from cullet as it does to produce it from raw materials. Float glass contains approximately 20% Cullet (recycled glass).

Cullet generated within the same plant and reintroduced to the original process does not qualify as pre-consumer recycled content. Additionally, in effort to maintain high-quality performance of our products, we do not introduce post-consumer recycled glass into our process. Thus, pre consumer and post-consumer recycled content of products is 0%.

Change Summary

Change	Date
Format Update; removal of Chemical Analysis section	04/29/2025
Format Update	09/15/2026

The information contained in this bulletin is offered for assistance in the application of Pilkington North America Inc. flat glass products, but **IT DOES NOT CONSTITUTE A WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE**. Actual performance may vary in particular applications.



Pilkington North America
811 Madison Ave Toledo, Ohio 43604-5684
buildingproducts.pna@nsg.com
800 221 0444
www.pilkington.us