

STRENGTH OF PILKINGTON TEXTURE GLASS

ATS-158
09/2026

Summary

The uniform load capacity of textured or patterned glass has been given various values in the glass literature. Theoretically a simple analysis could take the strength of a flat glass of the same thickness as the thinnest part of the patterned glass, but this approach is not valid because it does not take into account the stress concentration effect of sharp details in some patterns.

Pilkington Texture Glass patterns (except for Pilkington **Warwick™**) have been load tested and found to be at least 55% as strong as flat glass of the same nominal thickness.

For United States applications the uniform load capacity of flat glass is given in ASTM E 1300 standard for rectangular glass subjected to a uniform 3 second duration load. For example, a 48" x 96" light of 1/4" annealed glass, simply supported on all four edges has an 8 in 1000 breakage probability under a 3 second duration load of 29.7 psf according to E 1300. Using the 55% rule, the same size 6mm Pilkington Texture Glass will support a 3-second duration uniform load of $0.55 \times 29.7 = 16.3$ psf for an 8 in 1000 breakage probability.

Pilkington **Warwick™** texture glass has a textured surface with particular stress concentration details. The uniform load capacity of Pilkington **Warwick™** is taken as 35% of that of ASTM E 1300 glass of the same thickness.

Change Summary

Change	Date
Correction of load duration	05/19/2023
Format Update	04/10/2025
Format Update	09/15/2026

The information contained in this bulletin is offered for assistance in the application of Pilkington North America Inc. flat glass products, but **IT DOES NOT CONSTITUTE A WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE**. Actual performance may vary in particular applications.



Pilkington North America
811 Madison Ave Toledo, Ohio 43604-5684
buildingproducts.pna@nsg.com
800 221 0444
www.pilkington.us